

Technical data sheet

Chipboard Panel

RAW CHIPBOARD TECHNICAL CHARACTERISTICS

	Test Method	Unit	Value
Tolerance of edge straightness	EN 14323	mm/m	1,5
Planarity (both sides melamine faced)	EN 14323	mm/m	2
Moisture Content	EN 322	%	5 – 13
Tolerance of mean density within same panel	EN 323	%	±10
Formaldehyde Content (Perforator)	EN 120	mg/100g	≤8mg/100gr air

Properties	Measure Unit	Standard	Conditions							
			Nominal Panel Thickness (mm)							
			≥3 <4	≥4 <6	≥6 ≤13	>13 ≤20	>20 ≤25	>25 ≤32	>32 ≤40	>40
Bending Strength	N/mm ²	EN 310	13	14	13	13	11.5	10	8.5	7
Elasticity modulus	N/mm ²	EN 310	1800	1950	1800	1600	1500	1350	1200	1050
Internal Bonding	N/mm ²	EN 319	0,45	0,45	0,4	0,35	0,305	0,25	0,2	0,2
Density	Kg/m ³		500 - 700							

FIELD OF APPLICATION

Melamine Faced board manufactured with Type P2 raw boards is intended for use in interior fitting (including furnitures) for use in dry conditions (relative humidity should not exceed more than 65% for a few weeks per year). The components must allow quick release of any trapped moisture.

Melamine Faced board manufactured with Type P3 raw boards is intended for use under humid conditions (relative humidity should not exceed more than 85% for a few weeks per year). The components must allow quick release of any trapped moisture. Melamine faced boards are available in a wide range of decors and color matched edge banding.

GENERAL GUIDANCE

The boards should be advisably be stored on a flat and dry base in a self-contained building. The atmospheric humidity should no go over 75% for a long period of time. In case of longer storage periods under humid conditions the boards should shrink-wrapped to avoid swelling of the board's edges is advised. A continuous room temperature should be maintained between 10°C and 50°C.

RESISTANCE AGAINST HEAT

The resistance against heat has to be subdivided in long and short terms exposure. For long or continuous terms of heat exposure a maximum temperature of 50°C is allowed. A temperature of max. 90°C is allowed for a time period of not more than 1 hour. Long term temperature application of more that 50oC might damage the surface by cracks. Installations of technical equipment that emit heat require an appropriate distance between heat source and melamine surface to avoid heat accumulation and divert temperature.

STORAGE AND HANDLING

Goods must be stored in a dry and ventilated place (relative air humidity 35%-65%). Do not store with inflammable substances. If exposed to direct sunlight, the laminate may deteriorate. Stacks should be stored correctly, at a manageable height to ensure stability. To avoid warping or damp stains, place the panels on pallets with adequate spaces. When handling the laminates, use suction pads or gloves. Machinery and equipment must be fitted with suitable aspiration systems.

CLEANING AND MAINTENANCE

The melamine surfaces are the most resistant among those used in the furniture field. For cleaning, it is preferable to choose a detergent for domestic use. It is recommended that you avoid spraying products directly onto the surface, as this may leave stains and marks; instead, it is preferable to apply the detergent product on a soft damp cloth, clean the surface and then rinse it. Avoid using abrasive products, bleach or highly chlorinated products or acids.

Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies. The contents of this technical leaflet should therefore not be considered as instructions for use or as legally binding.